

D-K9-25

516640

n_d = 1.515770

υ_d = 63.99

n_e = 1.517694

υ_e = 63.79

n_F - n_C = 0.008060

n_{F'}- n_{C'} = 0.008115

折 射 率Refractive Index**		相 对 部 分 色 散Relative Partial Dispersions				内 部 透 过 率Internal Transmittance τ			
	λ（nm）					λ（nm）	τ（5mm）	τ（10mm）	
n _{2325.42}	2325.42		P _{s,t}	0.3128	P' _{s,t}	0.3107	2400	0.918	0.842
n _{1970.09}	1970.09		P _{C,s}	0.5635	P' _{C',s}	0.6087	2200	0.952	0.906
n _{1529.58}	1529.58		P _{d,C}	0.3081	P' _{d,C'}	0.2569	2000	0.989	0.978
n _{1060.0}	1060.0		P _{e,d}	0.2387	P' _{e,d}	0.2371	1800	0.995	0.990
n _t	1013.98		P _{g,F}	0.5339	P' _{g,F'}	0.4744	1600	0.997	0.995
n _s	852.11		P _{i,h}	0.7444	P' _{i,h}	0.7394	1400	0.991	0.982
n _r	706.52		异常色散 Abnormal Dispersions				1200	0.999	0.998
n _C	656.27		ΔP _{C,t}	0.0285	ΔP _{C,s}	0.0105	1060	0.999	0.998
n _{C'}	643.85		ΔP _{F,e}	-0.0016	ΔP _{g,F}	-0.0029	1000	0.999	0.998
n _{He-Ne}	632.8						950	0.999	0.998
n _D	589.29						900	0.999	0.998
n _d	587.56		着色度 Color Code				850	0.999	0.998
n _e	546.07		λ ₈₀ /λ ₅		315/280		800	0.999	0.998
n _F	486.13		λ ₇₀ /λ ₅				700	0.999	0.998
n _{F'}	479.99						650	0.999	0.998
n _g	435.83						600	0.999	0.997
n _h	404.66						550	0.998	0.996
n _i	365.01		热性质 Thermal Properties				500	0.998	0.996
n _{313.18}	313.18		T _g （℃）		496		480	0.998	0.996
n _{302.15}	302.15		T _s （℃）		558		460	0.998	0.996
			T ₁₀ ^{14.5} （℃）		451		440	0.998	0.996
			T ₁₀ ¹³ （℃）		483		420	0.998	0.996
			T ₁₀ ^{7.6} (℃)		637		400	0.998	0.996
			α _{-30/70℃} (10 ⁻⁷ /K)		63		390	0.997	0.994
			α _{100/300℃} (10 ⁻⁷ /K)		78		380	0.996	0.992
			λ[W/(m·K)]		1.018		370	0.994	0.989
			c _p [J/(g·K)]		0.813		360	0.990	0.981
							350	0.980	0.960
			化学性质 Chemical Properties				340	0.968	0.937
					Grade		330	0.927	0.860
			D _W		1		320	0.851	0.725
			D _A		2		310	0.710	0.504
			CR		1		300	0.498	0.248
			RC(S)		1		290	0.257	0.066
			RA(S)		2		280		
							机械性质 Mechanical Properties		
							H _K （10 ⁷ Pa）		492
							F _A		72
							E（10 ⁷ Pa）		8318
							G（10 ⁷ Pa）		3430
							μ		0.212
							B（10 ⁻¹² /Pa）		2.72
							其他性质 Other Properties		
							ρ（g/cm ³ ）		2.41
							备注 Remarks		
							**:退火速率 anneal rate 25℃/h		