

D-K9			516641			n _d = 1.516330		ν _d = 64.06		n _F - n _C = 0.008060				
						n _e = 1.518254		ν _e = 63.86		n _{F'} - n _{C'} = 0.008115				
折光率 Refractive Index*			相对部分色散 Relative Partial Dispersions				内部透过率 Internal Transmittance τ							
	λ (nm)		P _{s,t}	0.3128	P' _{s,t}	0.3107	λ (nm)	τ (5mm)	τ (10mm)					
n _{2325.42}	2325.42	1.488293	P _{C,s}	0.5635	P' _{C',s}	0.6087	2400	0.918	0.842					
n _{1970.09}	1970.09	1.494167	P _{d,C}	0.3081	P' _{d,C'}	0.2569	2200	0.952	0.906					
n _{1529.58}	1529.58	1.500265	P _{e,d}	0.2387	P' _{e,d}	0.2371	2000	0.989	0.978					
n _{1060.0}	1060.0	1.506155	P _{g,F}	0.5339	P' _{g,F'}	0.4744	1800	0.995	0.990					
n _t	1013.98	1.506784	P _{i,h}	0.7444	P' _{i,h}	0.7394	1600	0.997	0.995					
n _s	852.11	1.509305	异常色散 Abnormal Dispersions				1400	0.991	0.982					
n _r	706.52	1.512413					ΔP _{C,t}	0.0282	ΔP _{C,s}	0.0103	1200	0.999	0.998	
n _C	656.27	1.513847					ΔP _{F,e}	-0.0015	ΔP _{g,F}	-0.0027	1060	0.999	0.998	
n _{C'}	643.85	1.514245					1000	0.999	0.998					
n _{He-Ne}	632.8	1.514616					950	0.999	0.998					
n _D	589.29	1.516258					900	0.999	0.998					
n _d	587.56	1.516330	着色度 Color Code				850	0.999	0.998					
n _e	546.07	1.518254					λ ₈₀ /λ ₅	315/280			800	0.999	0.998	
n _F	486.13	1.521907					λ ₇₀ /λ ₅				700	0.999	0.998	
n _{F'}	479.99	1.522360					650	0.999	0.998					
n _g	435.83	1.526210					600	0.999	0.997					
n _h	404.66	1.529756					550	0.998	0.996					
n _i	365.01	1.535756	热性质 Thermal Properties				500	0.998	0.996					
n _{313.18}	313.18	1.547811					T _g (°C)	496			480	0.998	0.996	
n _{302.15}	302.15	1.551348	T _s (°C)	558			460	0.998	0.996					
			T ₁₀ ^{14.5} (°C)	451			440	0.998	0.996					
			T ₁₀ ¹³ (°C)	483			420	0.998	0.996					
			T ₁₀ ^{7.6} (°C)	637			400	0.998	0.996					
			α _{30/70℃} (10 ⁻⁷ /K)	63			390	0.997	0.994					
			α _{100/300℃} (10 ⁻⁷ /K)	78			380	0.996	0.992					
			λ[W/(m·K)]	1.018			370	0.994	0.989					
			c _p [J/(g·K)]	0.813			360	0.990	0.981					
							350	0.980	0.960					
			化学性质 Chemical Properties				340	0.968	0.937					
							Grade				330	0.927	0.860	
			D _W	1			320	0.851	0.725					
			D _A	2			310	0.710	0.504					
			CR	1			300	0.498	0.248					
			RC(S)	1			290	0.257	0.066					
			RA(S)	2			280							