

D-ZK3-25			588613			n _d = 1.588330		ν _d = 61.28		n _F - n _C = 0.009600					
						n _e = 1.590620		ν _e = 61.08		n _{F'} - n _{C'} = 0.009670					
折 射 率 Refractive Index**			相 对 部 分 色 散 Relative Partial Dispersions				内 部 透 过 率 Internal Transmittance τ								
	λ (nm)		P _{s,t}	0.3032	P' _{s,t}	0.3010	λ (nm)	τ (5mm)	τ (10mm)						
n _{2325.42}	2325.42	1.556588	P _{C,s}	0.5555	P' _{C',s}	0.6003	2400	0.847	0.717						
n _{1970.09}	1970.09	1.563055	P _{d,C}	0.3068	P' _{d,C'}	0.2557	2200	0.926	0.858						
n _{1529.58}	1529.58	1.569801	P _{e,d}	0.2385	P' _{e,d}	0.2368	2000	0.979	0.958						
n _{1060.0}	1060.0	1.576422	P _{g,F}	0.5374	P' _{g,F'}	0.4775	1800	0.989	0.979						
n _t	1013.98	1.577141	P _{i,h}	0.7537	P' _{i,h}	0.7483	1600	0.995	0.991						
n _s	852.11	1.580052	异常色散 Abnormal Dispersions				1400	0.992	0.984						
n _r	706.52	1.583692					ΔP _{C,t}	0.0237	ΔP _{C,s}	0.0089	1200	0.999	0.998		
n _C	656.27	1.585385					ΔP _{F,e}	-0.0016	ΔP _{g,F}	-0.0039	1060	0.999	0.998		
n _{C'}	643.85	1.585857					1000	0.999	0.998						
n _{He-Ne}	632.8	1.586296					950	0.999	0.998						
n _D	589.29	1.588244					900	0.999	0.998						
n _d	587.56	1.588330	着色度 Color Code				850	0.999	0.998						
n _e	546.07	1.590620	λ ₈₀ /λ ₅		345/285		800	0.999	0.998						
n _F	486.13	1.594985	λ ₇₀ /λ ₅				700	0.999	0.998						
n _{F'}	479.99	1.595527					650	0.999	0.998						
n _g	435.83	1.600144					600	0.998	0.997						
n _h	404.66	1.604408					550	0.998	0.997						
n _i	365.01	1.611644	热性质 Thermal Properties				500	0.998	0.997						
n _{313.18}	313.18	1.626253	T _g (°C)		511		480	0.998	0.996						
n _{302.15}	302.15	1.630556	T _s (°C)		546		460	0.998	0.996						
			T ₁₀ ^{14.5} (°C)		471		440	0.998	0.996						
			T ₁₀ ¹³ (°C)		499		420	0.997	0.995						
			T ₁₀ ^{7.6} (°C)		605		400	0.997	0.994						
			α _{30/70} °C(10 ⁻⁷ /K)		72		390	0.995	0.991						
			α _{100/300} °C(10 ⁻⁷ /K)		93		380	0.992	0.984						
			λ[W/(m·K)]		0.949		370	0.986	0.972						
			c _p [J/(g·K)]		0.732		360	0.972	0.945						
							350	0.946	0.894						
			化学性质 Chemical Properties				340	0.897	0.804						
					Grade		330	0.812	0.660						
			D _W		3		320	0.683	0.466						
			D _A		6		310	0.510	0.260						
			CR		4c		300	0.321	0.103						
			RC(S)		2		290	0.164	0.027						
			RA(S)		3		280	0.071	0.005						
							机械性质 Mechanical Properties								
							H _K (10 ⁷ Pa)		628						
							F _A		125						
							E (10 ⁷ Pa)		9767						
							G (10 ⁷ Pa)		3958						
							μ		0.234						
							B (10 ⁻¹² /Pa)		2.08						
							其他性质 Other Properties								
							ρ (g/cm ³)		2.83						
							备注 Remarks								
							**: 退火速率 anneal rate 25℃/h								