

H-ZF13GT			785257			n _d = 1.784720		ν _d = 25.72		n _F - n _C = 0.030510					
						n _e = 1.791906		ν _e = 25.51		n _{F'} - n _{C'} = 0.031041					
折 射 率 Refractive Index			相 对 部 分 色 散 Relative Partial Dispersions				内 部 透 过 率 Internal Transmittance τ								
	λ (nm)		P _{s,t}	0.2091	P' _{s,t}	0.2055	λ (nm)	τ (5mm)	τ (10mm)						
n _{2325.42}	2325.42	1.729717	P _{C,s}	0.4622	P' _{C',s}	0.4981	2400	0.939	0.882						
n _{1970.09}	1970.09	1.736237	P _{d,C}	0.2868	P' _{d,C'}	0.2381	2200	0.961	0.924						
n _{1529.58}	1529.58	1.743909	P _{e,d}	0.2355	P' _{e,d}	0.2315	2000	0.981	0.962						
n _{1060.0}	1060.0	1.754085	P _{g,F}	0.6157	P' _{g,F'}	0.5443	1800	0.988	0.977						
n _t	1013.98	1.755488	P _{i,h}		P' _{i,h}		1600	0.996	0.992						
n _s	852.11	1.761868	异常色散 Abnormal Dispersions				1400	0.997	0.995						
n _r	706.52	1.771216					ΔP _{C,t}	0.0039	ΔP _{C,s}	-0.0003	1200	0.999	0.998		
n _C	656.27	1.775970					ΔP _{F,e}	0.0022	ΔP _{g,F}	0.0138	1060	0.999	0.998		
n _{C'}	643.85	1.777330					1000	0.999	0.998						
n _{He-Ne}	632.8	1.778613					950	0.999	0.998						
n _D	589.29	1.784457					900	0.999	0.998						
n _d	587.56	1.784720	着色度 Color Code				850	0.999	0.998						
n _e	546.07	1.791906					λ ₈₀ /λ ₅	415/365			800	0.999	0.997		
n _F	486.13	1.806480					λ ₇₀ /λ ₅				700	0.998	0.996		
n _{F'}	479.99	1.808371					650	0.997	0.995						
n _g	435.83	1.825266					600	0.997	0.994						
n _h	404.66	1.842268					550	0.996	0.992						
n _i	365.01		热性质 Thermal Properties				500	0.991	0.982						
n _{313.18}	313.18						T _g (°C)	613			480	0.989	0.978		
n _{302.15}	302.15		T _s (°C)	646			460	0.986	0.972						
			T ₁₀ ^{14.5} (°C)	556			440	0.982	0.964						
			T ₁₀ ¹³ (°C)	593			420	0.972	0.945						
色散公式常数 Constants of Dispersion Formula			T ₁₀ ^{7.6} (°C)	707			400	0.937	0.878						
			α _{30/70} °C(10 ⁻⁷ /K)	86			390	0.880	0.775						
K ₁	1.73521591E+00		α _{100/300} °C(10 ⁻⁷ /K)	106			380	0.720	0.519						
L ₁	1.31087904E-02		λ[W/(m·K)]	0.841			370	0.346	0.120						
K ₂	3.16277446E-01		c _p [J/(g·K)]	0.619			360	0.122	0.015						
L ₂	6.21421663E-02						350								
K ₃	2.16384634E+00		化学性质 Chemical Properties				340								
L ₃	1.78845558E+02							Grade		330					
			D _W	1			320								
折射率温度系数常数 Constants of dn/dt			D _A	1			310								
			CR	1			300								
			RC(S)	1			290								
			RA(S)	1			280								