

H-ZF62			923209		n _d = 1.922860		ν _d = 20.88		n _F - n _C = 0.044198					
					n _e = 1.933224		ν _e = 20.70		n _{F'} - n _{C'} = 0.045079					
折射率 Refractive Index			相对部分色散 Relative Partial Dispersions				内部透过率 Internal Transmittance τ							
	λ (nm)		P _{s,t}	0.1973	P' _{s,t}	0.1935	λ (nm)	τ (5mm)	τ (10mm)					
n _{2325.42}	2325.42	1.848882	P _{C,s}	0.4462	P' _{C',s}	0.4802	2400	0.969	0.938					
n _{1970.09}	1970.09	1.856987	P _{d,C}	0.2821	P' _{d,C'}	0.2338	2200	0.981	0.962					
n _{1529.58}	1529.58	1.866679	P _{e,d}	0.2345	P' _{e,d}	0.2299	2000	0.990	0.979					
n _{1060.0}	1060.0	1.880056	P _{g,F}	0.6399	P' _{g,F'}	0.5651	1800	0.994	0.987					
n _t	1013.98	1.881950	P _{i,h}		P' _{i,h}		1600	0.997	0.995					
n _s	852.11	1.890672	异常色散 Abnormal Dispersions				1400	0.999	0.997					
n _r	706.52	1.903689					ΔP _{C,t}	-0.0011	ΔP _{C,s}	-0.0049	1200	0.999	0.998	
n _C	656.27	1.910392					ΔP _{F,e}	0.0053	ΔP _{g,F}	0.0298	1060	0.999	0.997	
n _{C'}	643.85	1.912319					1000	0.998	0.996					
n _{He-Ne}	632.8	1.914140					950	0.998	0.996					
n _D	589.29	1.922483					900	0.997	0.994					
n _d	587.56	1.922860	着色度 Color Code				850	0.997	0.994					
n _e	546.07	1.933224					λ ₈₀ /λ ₅				800	0.996	0.992	
n _F	486.13	1.954590					λ ₇₀ /λ ₅		430/385		700	0.995	0.990	
n _{F'}	479.99	1.957398					650	0.993	0.986					
n _g	435.83	1.982873					600	0.992	0.984					
n _h	404.66	2.009266					550	0.986	0.973					
n _i	365.01		热性质 Thermal Properties				500	0.972	0.944					
							T _g (°C)		720		480	0.964	0.929	
			T _s (°C)		751		460	0.953	0.908					
			T ₁₀ ^{14.5} (°C)		667		440	0.933	0.871					
			T ₁₀ ¹³ (°C)		699		420	0.894	0.799					
			T ₁₀ ^{7.6} (°C)		806		400	0.732	0.536					
			α _{-30/70℃} (10 ⁻⁷ /K)		64		390	0.459	0.211					
			α _{100/300℃} (10 ⁻⁷ /K)		77		380							
			λ[W/(m·K)]		0.639		370							
			c _p [J/(g·K)]		0.463		360							
							350							
			化学性质 Chemical Properties				340							
									Grade		330			
			D _W		1		320							
			D _A		1		310							
			CR		1		300							
			RC(S)		1		290							
			RA(S)		1		280							
		</												