

H-ZLaF89L			954323		n _d = 1.953750		ν _d = 32.31		n _F - n _C = 0.029520					
					n _e = 1.960736		ν _e = 32.07		n _{F'} - n _{C'} = 0.029953					
折 射 率 Refractive Index			相 对 部 分 色 散 Relative Partial Dispersions				内 部 透 过 率 Internal Transmittance τ							
	λ (nm)		P _{s,t}	0.2207	P' _{s,t}	0.2175	λ (nm)	τ (5mm)	τ (10mm)					
n _{2325.42}	2325.42	1.897018	P _{C,s}	0.4790	P' _{C',s}	0.5170	2400	0.926	0.858					
n _{1970.09}	1970.09	1.904150	P _{d,C}	0.2918	P' _{d,C'}	0.2426	2200	0.978	0.956					
n _{1529.58}	1529.58	1.912393	P _{e,d}	0.2367	P' _{e,d}	0.2332	2000	0.991	0.981					
n _{1060.0}	1060.0	1.923039	P _{g,F}	0.5906	P' _{g,F'}	0.5227	1800	0.997	0.994					
n _t	1013.98	1.924483	P _{i,h}	0.9489	P' _{i,h}	0.9352	1600	0.999	0.998					
n _s	852.11	1.930997	异常色散 Abnormal Dispersions				1400	0.999	0.998					
n _r	706.52	1.940406					ΔP _{C,t}	0.0012	ΔP _{C,s}	0.0009	1200	0.999	0.998	
n _C	656.27	1.945136					ΔP _{F,e}	-0.0004	ΔP _{g,F}	-0.0001	1060	0.999	0.998	
n _{C'}	643.85	1.946483					1000	0.999	0.998					
n _{He-Ne}	632.8	1.947750					950	0.999	0.998					
n _D	589.29	1.953493	着色度 Color Code				900	0.999	0.998					
n _d	587.56	1.953750					λ ₈₀ /λ ₅	405/360			850	0.999	0.998	
n _e	546.07	1.960736					λ ₇₀ /λ ₅				800		0.999	0.998
n _F	486.13	1.974656					700	0.998	0.997					
n _{F'}	479.99	1.976436					650	0.998	0.996					
n _g	435.83	1.992091					600	0.997	0.994					
n _h	404.66	2.007363					550	0.996	0.993					
n _i	365.01	2.035375	热性质 Thermal Properties				500	0.992	0.984					
n _{313.18}	313.18		T _g (°C)		708			480	0.988	0.977				
n _{302.15}	302.15		T _s (°C)		745			460	0.983	0.967				
			T ₁₀ ^{14.5} (°C)		649			440	0.975	0.951				
			T ₁₀ ¹³ (°C)		685			420	0.960	0.922				
			T ₁₀ ^{7.6} (°C)		800			400	0.926	0.857				
			α _{30/70℃} (10 ⁻⁷ /K)		72			390	0.889	0.791				
			α _{100/300℃} (10 ⁻⁷ /K)		88			380	0.823	0.678				
			λ[W/(m·K)]		0.753			370	0.694	0.481				
			c _p [J/(g·K)]		0.415			360	0.435	0.189				
							350	0.141	0.020					
							340							
							330							
折射率温度系数常数 Constants of dn/dt			D _W		1			320						
			D _A		1			310						
			CR		1			300						
			RC(S)		1			290						
			RA(S)		1			280						