

H-ZLaF89LA			954323		n _d = 1.953750		ν _d = 32.28		n _F - n _C = 0.029550					
					n _e = 1.960743		ν _e = 32.04		n _{F'} - n _{C'} = 0.029983					
折 射 率 Refractive Index			相 对 部 分 色 散 Relative Partial Dispersions				内 部 透 过 率 Internal Transmittance τ							
	λ (nm)		P _{s,t}	0.2207	P' _{s,t}	0.2176	λ (nm)	τ (5mm)	τ (10mm)					
n _{2325.42}	2325.42	1.896973	P _{C,s}	0.4791	P' _{C',s}	0.5172	2400	0.936	0.876					
n _{1970.09}	1970.09	1.904093	P _{d,C}	0.2918	P' _{d,C'}	0.2426	2200	0.982	0.964					
n _{1529.58}	1529.58	1.912338	P _{e,d}	0.2366	P' _{e,d}	0.2332	2000	0.992	0.985					
n _{1060.0}	1060.0	1.922999	P _{g,F}	0.5906	P' _{g,F'}	0.5226	1800	0.998	0.996					
n _t	1013.98	1.924446	P _{i,h}	0.9493	P' _{i,h}	0.9356	1600	0.999	0.998					
n _s	852.11	1.930969	异常色散 Abnormal Dispersions				1400	0.999	0.998					
n _r	706.52	1.940391					ΔP _{C,t}	0.0015	ΔP _{C,s}	0.0011	1200	0.999	0.998	
n _C	656.27	1.945126					ΔP _{F,e}	-0.0004	ΔP _{g,F}	-0.0001	1060	0.999	0.998	
n _{C'}	643.85	1.946475					1000	0.999	0.998					
n _{He-Ne}	632.8	1.947743					950	0.999	0.998					
n _D	589.29	1.953492					900	0.999	0.998					
n _d	587.56	1.953750	着色度 Color Code				850	0.999	0.998					
n _e	546.07	1.960743					λ ₈₀ /λ ₅				800	0.999	0.998	
n _F	486.13	1.974676	λ ₇₀ /λ ₅	405/355			700	0.999	0.998					
n _{F'}	479.99	1.976458					650	0.998	0.997					
n _g	435.83	1.992128					600	0.996	0.993					
n _h	404.66	2.007416					550	0.995	0.991					
n _i	365.01	2.035469	热性质 Thermal Properties				500	0.990	0.981					
n _{313.18}	313.18						T _g (°C)	733			480	0.986	0.973	
n _{302.15}	302.15		T _s (°C)	760			460	0.981	0.962					
			T ₁₀ ^{14.5} (°C)	680			440	0.972	0.944					
			T ₁₀ ¹³ (°C)	712			420	0.956	0.913					
			T ₁₀ ^{7.6} (°C)	817			400	0.915	0.838					
			α _{30/70} °C(10 ⁻⁷ /K)	71			390	0.875	0.766					
			α _{100/300} °C(10 ⁻⁷ /K)	89			380	0.800	0.640					
			λ[W/(m·K)]	0.753			370	0.647	0.418					
			c _p [J/(g·K)]	0.420			360	0.354	0.125					
							350							
			化学性质 Chemical Properties				340							
								Grade			330			
			D _W	1			320							
			D _A	1			310							
			CR	1			300							
			RC(S)	1			290							
			RA(S)	2			280							